

Europäisches Patentamt

European Patent Office

Office européen des brevets



EP 0 950 723 A1

(12)

EUROPEAN PATENT APPLICATION

published in accordance with Art. 158(3) EPC

- (43) Date of publication: 20.10.1999 Bulletin 1999/42
- (21) Application number: 97946091.2
- (22) Date of filing: 03.12.1997

- (51) Int. Cl.6: C22C 38/00, C22C 38/24, C23C 8/32; C23C 8/34
- (86) International application number: PCT/JP97/04430
- (87) International publication number: WO 98/27242 (25.06.1998 Gazette 1998/25)

- (84) Designated Contracting States: **DE GB**
- (30) Priority: 17.12.1996 JP 35415096
- (71) Applicant: KOMATSU LTD. Minato-ku, Tokyo 107 (JP)
- (72) Inventors:
 - TAKAYAMA, Takemori Komatsu Ltd. Hirakata-shi Osaka 573 (JP)

- HAMASAKA, Naoji Komatsu Ltd. Hirakata-shi Osaka 573 (JP)
- (74) Representative: Viering, Jentschura & Partner Postfach 22 14 43 80504 München (DE)

HIGH BEARING-STRENGTH STEEL PARTS AND PROCESSES FOR THE PRODUCTION (54)**THEREOF**

High surface pressure resistant steel parts and (57)their producing methods are disclosed. These steel parts are useful as gears, cams, bearings and similar high-strength compact steel articles which are required to have wear resistance and strength to withstand fatigue in rolling or rolling-slipping applications. In a steel part formed according to the invention, a fine nitride and/or carbonitride having at least an average grain size of 0.3 µm or less is dispersed in the contact surface structure; a multi phase structure composed of martensite, which is divided into extremely fine pieces, forming a disordered shape, by the nitride and/or carbonitride, is formed; and a carbide having a grain size of 3 µm or less is dispersed to increase the hardness of the surface. Such a steel part is produced by carrying out carbonitriding or carburization/carbonitriding so as to precipitate extremely fine AIN, using nitrogen permeating from the surface and by carrying out quenching or quenching/tempering, starting from a temperature region where the parent phase is austenite

FIG. 3

